

Prüfbericht - Nr.: 21128415 002

Seite 1 von 45

Test Report No.:

Page 1 of 45

Auftraggeber: Weldas Europe B.V.
Client: De Poort 77, 4411 PB Rilland, Netherland

Gegenstand der Prüfung: Protective gloves for welders
Test item:

Bezeichnung: siehe Sonstiges
Identification: see other aspects
Serien-Nr.: 1027544
Serial No.:

Wareneingangs-Nr.: 744-700380/01
Receipt No.:
Eingangsdatum: 15.02.2007
Date of receipt:

Prüfört: TRPS / Prüfstelle für Produktsicherheit Leipzig
Testing location: Maximilianallee 4, 04129 Leipzig, Fon/Fax: +49 341 600 369-0 / -10

Prüfgrundlage: DIN EN 12477/09.2005, DIN EN 420/2003
Test specification:

Prüfergebnis: Der Prüfgegenstand entspricht oben genannter Prüfgrundlage(n).
Test Result: The test item passed the test specification(s).

Prüflaboratorium: TRPS / Prüfstelle für Produktsicherheit Leipzig
Testing Laboratory:

geprüft/ tested by:

kontrolliert/ reviewed by:

11.04.2007 Albrecht/Expert



11.04.2007

Knape/General Manager Leipzig



Datum	Name/Stellung	Unterschrift
Date	Name/Position	Signature
11.04.2007	Albrecht/Expert	

Datum	Name/Stellung	Unterschrift
Date	Name/Position	Signature
11.04.2007	Knape/General Manager Leipzig	

Sonstiges/ Other Aspects:

Art.	Typ	Performance levels:	mechanical	4133	thermal	413X3X
Art. 10-2000	Typ A			4233		423X4X
Art. 10-2900	Typ A			4133		41344X
Art. 10-2385	Typ A			3133		313X4X
Art. 10-2850	Typ A/B			4143		423X4X
Art. 10-2750	Typ A/B			4133		413X3X
Art. 10-2087	Typ A/B			4133		413X3X
Art. 10-2178	Typ A			3124		413X4X
Art. 10-2392	Typ A/B			3134		413X4X
Art. 10-2101	Typ A/B			3121		413X4X
Art. 10-1003	Typ A/B			2122		412X4X
Art. 10-1005	Typ A/B			2111		412X4X
Art. 10-1007	Typ B			2111		412X4X
Art. 10-1009	Typ B			2133		413X4X
Art. 10-2304	Typ A/B					

Abkürzungen: P(ass) = entspricht Prüfgrundlage
F(all) = entspricht nicht Prüfgrundlage
N/A = nicht anwendbar
N/T = nicht getestet

Abbreviations: P(ass) = passed
F(all) = failed
N/A = not applicable
N/T = not tested

Dieser Prüfbericht bezieht sich nur auf das o.g. Prüfmuster und darf ohne Genehmigung der Prüfstelle nicht auszugsweise vervielfältigt werden. Dieser Bericht berechtigt nicht zur Verwendung eines Prüfzeichens.

This test report relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products.

Prüfbericht - Nr.: 21128415 002
Test Report No.: 744-700380/01

Seite 2 von 45
 Page 2 of 45

Used measuring instruments

Measuring	Device-Number Inventory-Number Serial-Number	next Calibration
Chromium VI content, Azo dye stuff		accredited test laboratory
Sizing	744 00 161	05/2008
Dexterity	744 00 197	05/2008

Test results of accredited laboratories of competent subcontractor are marked with /*.

already certified articles:

10-2000 Test report M 9811321 E01, 744-800242, dtd. 22.05.1998,
 10-2087
 10-2178

10-2900 Test report M 9910845 E01, 744-900170, dtd. 07.04.1999
 10-2392

10-2385 Test report M 9910393 E01, 744-800515, dtd. 04.03.1999
 10-2850
 10-2750
 10-2101
 10-1003
 10-1005
 10-1007
 10-1009
 10-2304

Prüfbericht - Nr.: 21128415 002
 Test Report No.: 744-700380/01

Seite 42 von 45
 Page 42 of 45

Art. 10-2304 Deersosoft

material:

palm deer grain leather
 back deer grain leather
 lining without
 cuff split cowhide leather



Parameter	according EN 12477	Requirement	Test result	Remark																											
				P	F	N/A	N/T																								
Glove design and construction General	clause 3 EN 420, 4.1	- in foreseeable conditions of use, protection at highest possible level - minimal time for put on/take off - overall not significantly decreased by seams	given			P																									
Resistance to water penetration	clause 3 EN 420, 4.2	if required, leather: <table border="1" style="display: inline-table; vertical-align: middle;"><thead><tr><th>level</th><th>penetration time [min]</th></tr></thead><tbody><tr><td>1</td><td>30</td></tr><tr><td>2</td><td>60</td></tr><tr><td>3</td><td>120</td></tr><tr><td>4</td><td>180</td></tr></tbody></table> textil:	level	penetration time [min]	1	30	2	60	3	120	4	180	-			N/A															
level	penetration time [min]																														
1	30																														
2	60																														
3	120																														
4	180																														
Innocuousness of protective gloves General	clause 3 EN 420, 4.3.1	- protection at use without harm to user - all substances contained which are known to cause allergies are named	given			P																									
Determination of pH-value	clause 3 EN 420, 4.3.2	>3,5 and < 9,5	given (see M 9910393 E01)			P																									
Determination of chromium (VI) content Azo dye stuff	clause 3 EN 420, 4.3.3	under detection limit 3 mg/kg under detection limit 30 mg/kg	/* AZ 24740 deer leather < 3 mg/kg cow split leather < 3 mg/kg cow split leather < 30 mg/kg			P																									
Determination of extractable protein content	clause 3 EN 420, 4.3.4	natural rubber: Lowry- test method: under detection limit	-			N/A																									
Cleaning	clause 3 EN 420, 4.4	no negative influence of performance levels after cleaning	-			N/A																									
Comfort and efficiency Sizing	clause 3 EN 420, 5.1.2	<table border="1" style="display: inline-table; vertical-align: middle;"><thead><tr><th>Hand size</th><th>minimum length [mm]</th></tr></thead><tbody><tr><td>6</td><td>300</td></tr><tr><td>7</td><td>310</td></tr><tr><td>8</td><td>320</td></tr><tr><td>9</td><td>330</td></tr><tr><td>10</td><td>340</td></tr><tr><td>11</td><td>350</td></tr></tbody></table>	Hand size	minimum length [mm]	6	300	7	310	8	320	9	330	10	340	11	350	<table border="1" style="display: inline-table; vertical-align: middle;"><thead><tr><th>Size</th><th>Length [mm]</th></tr></thead><tbody><tr><td>M/8</td><td>320</td></tr><tr><td>L/9</td><td>330</td></tr><tr><td>XL/10</td><td>340</td></tr><tr><td>XXL/11</td><td>350</td></tr></tbody></table>	Size	Length [mm]	M/8	320	L/9	330	XL/10	340	XXL/11	350			P	
Hand size	minimum length [mm]																														
6	300																														
7	310																														
8	320																														
9	330																														
10	340																														
11	350																														
Size	Length [mm]																														
M/8	320																														
L/9	330																														
XL/10	340																														
XXL/11	350																														
Special applications	clause 5.1.3	- fit for special purpose (clearly stated in instruction for use) - type of protective gloves - after each test, the inside material have to be checked of damage	type A and B given			P																									

Prüfbericht - Nr.: 21128415 002
Test Report No.: 744-700380/01

Seite 43 von 45
 Page 43 of 45

Art. 10-2304 Deersosoft

Parameter	according EN 12477	Requirement	Test result	Remark															
				P	F	N/A	N/T												
Water vapour transmission Water vapour absorption	EN 420, clause 5.3	if practicable, water vapour transmission allowed if required, leather: WVT: $\geq 5 \text{ mg}/(\text{cm}^2\cdot\text{h})$. if protection level inhibits or excludes water vapour transmission, effect of perspiration is reduced if required, leather: WVA: $\geq 8 \text{ mg}/\text{cm}^2$ for 8 h	given				P												
Abrasion resistance	clause 5.1	type A at least level 2 type B at least level 1 <table border="1"> <thead> <tr> <th>performance level</th> <th>abrasion (cycles)</th> </tr> </thead> <tbody> <tr><td>1</td><td>100</td></tr> <tr><td>2</td><td>500</td></tr> <tr><td>3</td><td>2000</td></tr> <tr><td>4</td><td>8000</td></tr> </tbody> </table>	performance level	abrasion (cycles)	1	100	2	500	3	2000	4	8000	/* 21128415 001 breakthrough at about [cycles] deer leather 500-2000 lowest value for classification: > 500				P perf. level 2		
performance level	abrasion (cycles)																		
1	100																		
2	500																		
3	2000																		
4	8000																		
Blade cut resistance	clause 5.2	type A at least level 1 type B at least level 1 <table border="1"> <thead> <tr> <th>performance level</th> <th>blade cut resist. (index)</th> </tr> </thead> <tbody> <tr><td>1</td><td>1,2</td></tr> <tr><td>2</td><td>2,5</td></tr> <tr><td>3</td><td>5,0</td></tr> <tr><td>4</td><td>10,0</td></tr> <tr><td>5</td><td>20,0</td></tr> </tbody> </table>	performance level	blade cut resist. (index)	1	1,2	2	2,5	3	5,0	4	10,0	5	20,0	/* 21128415 001 index i: 1,5 1,7 1,6 1,6 1,5 index I: 1,6 lowest Index I for classification: 1,6				P perf. level 1
performance level	blade cut resist. (index)																		
1	1,2																		
2	2,5																		
3	5,0																		
4	10,0																		
5	20,0																		
Tear resistance	clause 5.3	type A at least level 2 type B at least level 1 <table border="1"> <thead> <tr> <th>performance level</th> <th>Tear [N]</th> </tr> </thead> <tbody> <tr><td>1</td><td>10</td></tr> <tr><td>2</td><td>25</td></tr> <tr><td>3</td><td>50</td></tr> <tr><td>4</td><td>75</td></tr> </tbody> </table>	performance level	Tear [N]	1	10	2	25	3	50	4	75	/* 21128415 001 several values deer leather 73 62 lowest value for classification: 62				P perf. level 3		
performance level	Tear [N]																		
1	10																		
2	25																		
3	50																		
4	75																		
Puncture resistance	clause 5.4	type A at least level 2 type B at least level 1 <table border="1"> <thead> <tr> <th>performance level</th> <th>puncture [N]</th> </tr> </thead> <tbody> <tr><td>1</td><td>20</td></tr> <tr><td>2</td><td>60</td></tr> <tr><td>3</td><td>100</td></tr> <tr><td>4</td><td>150</td></tr> </tbody> </table>	performance level	puncture [N]	1	20	2	60	3	100	4	150	/* 21128415 001 several values 166 136 lowest value for classification: 136				P perf. level 3		
performance level	puncture [N]																		
1	20																		
2	60																		
3	100																		
4	150																		

Prüfbericht - Nr.: 21128415 002
Test Report No.: 744-700380/01

Seite 44 von 45
Page 44 of 45


Art. 10-2304 Deersosoft

Parameter	according EN 12477	Requirement	Test result	Remark			
				P	F	N/A	N/T
Burning behaviour	clause 5.5	type A at least level 2 type B at least level 1 Performance after flame time [s] after glow time [s] <hr/> 1 < 20 no requirements 2 < 10 < 120 3 < 3 < 25 4 < 2 < 5 The seams at heated area do not open after burning time of 15 s.	/* 21128415 001 after flame time 2 s after glow time 1 s no seams opening no melted dropping no melting at inner layer no whole formation	P			
Contact Heat	clause 5.6	type A at least level 1 type B at least level 1 performance- contact temp. threshold level <hr/> T _c [°C] t _t [s] 1 100 ≥ 15 2 250 ≥ 15 3 350 ≥ 15 4 500 ≥ 15	/* 21128415 001 glove palm at 100 °C 19 s at 250 °C 11 s	P			perf. level 1
Convective Heat	clause 5.7	type A at least level 2 type B at least level 0 Performance level Heat transfer index HTI <hr/> 1 ≥ 4 2 ≥ 7 3 ≥ 10 4 ≥ 18	/* 21128415 001 glove back 11 s cuff 11 s	P			perf. level 3
Impact of molten metal drops	clause. 5.8	type A at least level 3 type B at least level 2 performance level number of drops <hr/> 1 ≥ 10 2 ≥ 15 3 ≥ 25 4 ≥ 35	> 40 (see M 9910393 E01)	P			perf. level 4
Dexterity	clause 5.9	type A at least level 1 type B at least level 4 Performance smallest diameter of level pin <hr/> 1 11 2 9,5 3 8 4 6,5 5 5	pin:5 mm	P			perf. level 5
Optional Electrostatic properties (vertical resistance)	clause 3.4 and EN 1149-2	vertical resistance between inner and outer side > 10 ⁵ Ω	-				N/T

Prüfbericht - Nr.: 21128415 002
Test Report No.: 744-700380/01

Seite 45 von 45
 Page 45 of 45

Marking and Information according to EN 420/EN 12477 of gloves

Parameter	according EN 12477	Requirement	Test result	Remark			
				P	F	N/A	N/T
Marking	clause 6	<ul style="list-style-type: none"> - name, trade mark or other means of identification of the manufacturer - article identification - size - if required, best use before - EN 12477:2003 - figures: Protective gloves for welders: 	given				P
Information of the manufacturer	clause 7	<ul style="list-style-type: none"> - name, trade mark or other means of identification of the manufacturer - glove type , name or code for identification - size - if the expected shelf-life of the gloves is reduced by aging, the expiration date have to be added - the pictograms - if protection is only given, for part of gloves, information have to be added - possible problems - instruction for use for gloves and also for use with combination of other PPE - care label - information about penetration of UV-radiation and behaviour at arc welding - testing institute 	given given given not applicable given given given given given given given				P